



Mapelastick AquaDefense



Ready-to-use, ultra-quick drying, flexible liquid membrane for internal and external waterproofing applications



WHERE TO USE

To form waterproofing layers before applying ceramic, stone and mosaic coatings in:

- balconies and terraces;
- bathrooms and shower cubicles;
- laundry rooms;
- saunas and damp environments in general.

Mapelastick AquaDefense may be applied on:

- concrete;
- cementitious screeds and screeds made using special binders (**Topcem**, **Topcem Pronto**, **Mapecem** or **Mapecem Pronto**);
- plasterboard (for internal applications only);
- existing coatings in ceramic, terrazzo and stone;
- cementitious render.

ADVANTAGES

Mapelastick AquaDefense offers the following advantages:

- no drill or mixing tools required, supplied ready-to-use;
- resistant to rainwater 1 hour after applying the first coat and 3 hours after the second coat;
- ceramic coatings may be laid just 4 hours after applying the final coat (times refer to +23°C and 50% relative humidity of the air when the product is applied on dried screeds with a residual moisture lower than 3%).

TECHNICAL CHARACTERISTICS

Mapelastick AquaDefense is a totally solvent-free, ready-to-use ultra-quick drying, one-component light blue synthetic resin based paste in water dispersion.

Mapelastick AquaDefense is easy to apply using a long-haired roller, brush or trowel on horizontal, sloping and vertical surfaces. **Mapelastick AquaDefense** dries very quickly to form a flexible membrane without a sticky surface. It is resistant to light pedestrian traffic after just 3 hours and forms an excellent grip with all types of adhesive for laying ceramic, stone material and mosaic of all kinds. The flexible nature of **Mapelastick AquaDefense** helps it withstand normal movements caused by expansion and shrinkage of the substrate due to temperature variations and vibration.

Tiles installed on floors waterproofed with **Mapelastick AquaDefense** by using C2F-class MAPEI adhesives (such as **Keraquick S1** or **Granirapid**.) and grouted with **Ultracolor Plus** may be opened to pedestrian traffic within 12 hours of starting the work. Times refer to the temperature and humidity conditions as indicated before.

Mapelastick AquaDefense is resistant to water, lime-water (pH > 12), water containing chlorine and detergents commonly used for cleaning residential environments.



Mapelastick AquaDefense



Impregnating Drain Vertical fabric with Mapelastick AquaDefense



Application of Mapeband on a wall-floor fillet joint with Mapelastick AquaDefense



Application of the first coat of Mapelastick AquaDefense on a screed

Mapelastick AquaDefense is certified to AS/NZS 4858:2004 Wet Area Membranes - CLASS III (CSIRO Test Report No. 8066A)

Mapelastick AquaDefense is certified to AS 4654.1-2012 for external above-ground use as a non-exposed waterproofing membrane (CSIRO Test Report No. 8056)

RECOMMENDATIONS

- Do not apply **Mapelastick AquaDefense** if the temperature is lower than +5°C.
- **Mapelastick AquaDefense** must always be covered with ceramic, mosaic or stone.
- Do not apply **Mapelastick AquaDefense** on cementitious substrates or on substrates with residual humidity higher than 3% and recurring rising damp.
- Do not apply **Mapelastick AquaDefense** on crumbly cementitious substrates, old floors which are not well bonded to the substrate or surface treatments which impede a good bond.
- Do not use **Mapelastick AquaDefense** to cover cracks.
- Protect the surface from rain for at least 1 hour after applying the first coat and 3 hours after applying the second coat (times refer to +23°C and 50% relative humidity of the air when the product is applied on dried screeds with a residual moisture lower than 3%).

APPLICATION PROCEDURE

Preparation of the substrate

Substrates must be well-cured, sound, clean, dry and free of oil, grease, cement laitance, old paint and any other substance which could compromise the bond. Cementitious substrates must be stable and dry with no rising damp. Surface dust must be completely removed.

Smoothing and levelling layers may be applied using **Planitop Fast 330** or **Adesilex P4**.

On old ceramic floors with hollowed or empty tile joints, or whenever slopes on surfaces need to be levelled out before spreading on **Mapelastick AquaDefense**, we recommend applying a smoothing and levelling layer using **Adesilex P4**. Substrates in this condition must be thoroughly checked and all coatings, such as wax, water-repellent treatments, etc. must be removed from the surface with a suitable cleaning product and/or by abrasion. If the substrate has micro-cracks, insert **Mapetex Sel** between the two coats of **Mapelastick AquaDefense**.

Before applying **Mapelastick AquaDefense**, pay particular attention to expansion joints and fillet joints between horizontal and vertical surfaces. In such cases, apply **Mapeband** and suitable profiles bonded in place with **Mapelastick AquaDefense**.

To waterproof drains on terraces and balconies, use the special kits from the **Drain** range. Structural joints must be waterproofed with **Mapeband TPE** bonded to the substrate with **Adesilex PG4**.

APPLICATION OF THE PRODUCT

Mapelastick AquaDefense must be applied in two even, coats (approx. 0.4 mm per coat) with a long-haired roller, brush or trowel. Wait until the first coat is dry, making sure the product becomes darker with a matt finish, before applying the second coat diagonally to the first (approximately 1 hour at +23°C and 50% relative humidity of the air and with substrates having residual humidity lower than 3%).

The final thickness of the two coats of **Mapelastick AquaDefense** must be at least 0.8 mm in order to create a robust, flexible and continuous film. Make sure there are no interruptions in the film caused by imperfections in the substrate.

If **Mapelastick AquaDefense** is applied to form an anti-fracture membrane on cracked substrates, we recommend inserting **Mapetex Sel** reinforcement in to the first coat while it is still fresh.

Mapetex Sel must be pressed down with a bubble-breaker roller on the first coat of **Mapelastick AquaDefense** while it is still fresh.

Wait until the first coat is dry then apply the second coat in order to completely embed **Mapetex Sel**.

Drying times may increase as **Mapetex Sel** insertion increases the final thickness of the applied film.

In bathrooms, on balconies, in saunas and Turkish baths, a water-tightness test may be carried out 12 hours after applying the final coat of **Mapelastick AquaDefense**.

Ceramic, stone and mosaic tiles may be installed 4 hours after applying the second coat (at +23°C and 50% relative humidity of the air) using a C2-class MAPEI adhesive according to EN 12004 standards, to be selected according to the final use of the floor or coating. For example, on balconies use **Keraflex Maxi S1** (class C2TE S1). For quickly laying tiles use **Keraquick S1** (Class C2FT S1) or **Granirapid** (Class C2F S1) and for laying all types of mosaic use **Kerabond Plus** mixed with **Isolastic 50** (Class C2T S1).

Grout tile joints with a special cementitious grout such as **Ultracolor Plus** - Class CG2WA, **Keracolor FF**, **Keracolor GG** mixed with **Fugolastic**) or epoxy grout (for example **Kerapoxy**, **Kerapoxy Design** Class RG). Seal expansion joints with a special MAPEI sealant (such as **Mapesil AC**, **Mapeflex PU45 FT** or **Mapesil LM** according to requirements).

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

Consistency:	paste
Colour:	light blue
Density (g/cm ³):	1.30
pH:	9.5
Dry solids content:	66
Brookfield Viscosity (mPa·s):	45,000 (spindle 6 - 10 rpm)

APPLICATION DATA (at +23°C - 50% R.H.)

Minimum filming temperature:	+5°C
Recommended application temperature:	from +5°C to +35°C
Waiting time between first and second coat:	approximately 60 minutes (when dry to the touch)
Waiting time before laying coating:	3-4 hours
Complete drying of 1 mm thick layer:	12 hours

FINAL PERFORMANCE

	EN 14891 acceptance range	Performance figures for Mapelastac AquaDefense
Initial bond strength EN 14891-A.6.2 (N/mm ²):	> 0.5	1.7
Bond strength after immersion in water (EN 14891-A.6.3) (N/mm ²):	> 0.5	> 1.0
Bond strength after application of heat source (EN 14891-A.6.5) (N/mm ²):	> 0.5	> 1.8
Bond strength after freeze-thaw cycles (EN 14891-A.6.6) (N/mm ²):	> 0.5	> 0.9
Bond strength after immersion in basic water (solution saturated with lime) (EN 14891-A.6.9) (N/mm ²):	> 0.5	> 1.3
Bond strength after immersion in sodium hypochlorite solution (EN 14891-A.6.7) (N/mm ²):	> 0.5	> 1.2
Crack-bridging ability at +23°C (EN 14891-A.8.2) (mm):	> 0.75	3.2
Crack-bridging ability at -5°C (EN 14891-A.8.3) (mm):	> 0.75	1.6
Impermeability to water under pressure (EN 14891-A.7) (1500 kPa):	no penetration	no penetration



Application by roller of Mapelastac AquaDefense second coat



Application of Mapelastac AquaDefense by brush between floor and wall before applying Mapeband



Bonding tiles on Mapelastac AquaDefense

Bond values according to EN 14891 measured using **Mapelastac AquaDefense** and a C2-type cementitious adhesive according to EN 12004

Mapelastic AquaDefense

Before laying the tiling, carefully check the surface of **Mapelastic AquaDefense** to make sure it is continuous and that there are no pin-holes or small craters. If there are such defects, apply a further coat where they are located.

Cleaning

Mapelastic AquaDefense may be removed easily from tools and surfaces while still fresh with water.

CONSUMPTION

1 kg/m² for two coats (1.3 kg/m² per mm of thickness).

PACKAGING

15 kg rectangular buckets.

STORAGE

Mapelastic AquaDefense may be stored for up to 24 months in its original packaging in a dry place. Protect from freezing weather.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapelastic AquaDefense is not considered dangerous according to the current regulations regarding the classification of mixtures. It is however recommended to use gloves, eyes protection and to take the usual precautions for handling chemical products.

For further and complete information about the safe use of our product please refer to the latest version of our Safety Data Sheet available from www.mapei.com.au.

PRODUCT FOR PROFESSIONAL USE.

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com.au

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com.au

ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.

All relevant references for the product are available upon request and from www.mapei.com.au



BUILDING THE FUTURE